



Technical Data Sheet

Koppers Inc.
Technical Center
1005 William Pitt Way
Pittsburgh, PA 15238-1362
412 826 3970
www.koppers.com



Grade L1

Property	Units	Value
Density	[g/cc]	0.38
Compressive Strength	MPa	3.4
Compressive Modulus	GPa	0.31
Tensile Strength	MPa	7.95
Tensile Modulus	GPa	0.31
Flexural Strength	MPa	3.2
Flexural Modulus	GPa	0.26
Shear Strength	MPa	0.67
Shear Modulus	GPa	0.09
Coefficient of Thermal Expansion	$E^{-6}/^{\circ}C @ 650^{\circ}C$	3.0
Thermal Conductivity - Z	W/m·K	70
Electrical Resistivity - Z	$\mu\Omega\cdot m$	47.6
Average Pore Size	μm	600
Average Pore Volume	%	70