



**PACIFIC TESTING LABORATORIES, INC.**

24950 Avenue Tibbitts, Valencia, CA 91355-3426, USA

TEL: (661) 257-1437

FAX: (661) 257-2411

Customer: Lawrence Berkley

Page 1 of 4

Test Date: 4-27-2007


Work Order: 34430

Material: Panel


Specimen	Width (inches)	Thickness (inches)	Maximum Load (pounds)	Maximum Stress (psi)	Poisson's Ratio	Modulus (psi)	Ultimate Extension %
1	0.525	0.0270	2,607	183,900	0.015	5.7E+07	0.35
2	0.544	0.0275	2,502	167,200	0.015	5.6E+07	0.31
3	0.521	0.0263	2,262	165,200	0.015	5.1E+07	0.33
			Average :	172,100	0.015	5.5E+07	0.33

This report applies only to the sample(s) tested and is not necessarily indicative of the quality or condition of apparently identical or similar products. As a mutual protection to clients, the public and Pacific Testing Laboratories, Inc., this report is submitted and accepted for the exclusive use of the client to whom it is addressed and upon the condition that it is not to be used, in whole or in part, in any advertising or publicity matter without prior written authorization from Pacific Testing Laboratories, Inc.

**Tensile Strength, Modulus, and Poisson's Ratio**  
Lawrence Berkeley Labs, Wo 34430  
Specimen # 1



**Tensile Strength, Modulus, and Poisson's Ratio**  
Lawrence Berkeley Labs, Wo 34430  
Specimen # 2



**Tensile Strength, Modulus, and Poisson's Ratio**  
Lawrence Berkeley Labs, Wo 34430  
Specimen # 3

